

E-TARP 85% Black

Technical Specifications

Properties	Test Method	Results
Fabric	—	Woven Polypropylene
Construction		20 x 17
Weight (OZ)	ASTM D- 3776	4.3 sq/yd
Grab (LBS)	ASTM D- 1682	W-230, F-165
Trap Tear (LBS)	ASTM D- 2261	W-90, F-70
Burst (PSI)	ASTM D- 3786	435
Puncture (LBS)	ASTM D- 3787	100
Elongation (%)	ASTM D-1682	W-18
Permeability	ASTM D- 737	450 cfm



800-659-5111



Indian Valley Industries, Inc.

Quality and Service Since 1940