E-TARP 85% White FR

Technical Specifications

Properties	Test Method	Results
Fabric	–	Woven Polypropylene
Weight (OZ)	ASTM D- 3776	5.7 sq/yd
Count (INS)		21 Ends, 22 Picks
Burst (PSI)	ASTM D- 3786	490
Tensile (LBS)	ASTM D- 4632	W-300, F-265
Puncture (LBS)	ASTM D- 4833	100
UV Resistant	XFTM 141H-6152	>85% - 500 hrs.
Permeability	ASTM D- 737	375 cfm
Flame Resist.	FTM - LS125-B	Zero Burn
Flame Resist.	DOT 302	Passed



800-659-5111

Indian Valley Industries, Inc.

Quality and Service Since 1940