TECHNICAL DATA SHEET

IVI 3617W Wire Back Silt Fence

Roll Size: 3' x 100'

Stakes: 1.5" x 1.5" x 48" Pointed Hardwood Stakes

Stake Spacing: 6' on center

Wire: 14 gauge, 4" x 4" galvanized welded wire

Attachment: Hog rings at top and mid-section on 24" spacing

A woven polypropylene fabric will meet or exceed the following typical values when tested in accordance with the proper ASTM test methods. Complies to AASHTO specification M-288 and ASTM D6461.

PRODUCT TEST DATA		
Physical Property	Test Method	MARV
Composition		Polypropylene
Color		Black
Tensile Strength - Grab	ASTM D-4632	124 lbs x 105 lbs (551.6 x 467.3 N)
Elongation	ASTM D-4632	15%
CBR Puncture	ASTM D-6241	300 lbs (1335 N)
Trapezoidal Tear	ASTM D-4533	65 x 65 lbs. (289.1 x 289.1 N)
U.V Resistance % Retained (500 hrs)	ASTM D-4355	70%
Apparent Opening Size (AOS)	ASTM D-4751	30 US Std. Sieve
Permittivity	ASTM D-4491	0.05 Sec-1
Water Flow Rate	ASTM D-4491	10 gal/min/ft ² (407.4 lpm/m ²)

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when agreed to in writing for specific conditions of use, no warranty or guarantee expressed or implied is made regarding the performance of any product, since the manner of use and handling are beyond our control. Nothing contained herein is to be construed as permission or as a recommendation to infringe any patent.